



## Reference test block JIS Z 2343



### Product characteristics

- Consists of two rectangular plates
- Plates with a uniform nickel-chromium coating (on a brass base) with transverse cracks.
- The thickness of the coating and therefore the crack depth vary from 10 to 50 µm depending on the application

Penetrant	Nickel-chrome layer
Red	50 µm, 30 µm
Fluorescent, Level 2	50 µm , 30 µm, 20 µm
Fluorescent, Level 3	30 µm, 20 µm, 10 µm
Fluorescent, Level 4	20 µm, 10 µm

Nickel-chrome layer	Item no.
10 µm	268
20 µm	1549
30 µm	137
40 µm	1842

A reference photo of the control body is required for monitoring the test equipment. This and the test certificate are included in the scope of delivery.

\*\*Technical changes reserved!\*\*