


MR[®] 76 FA Magnetic Powder Suspension



Product characteristics

- Ready-to-use magnetic particle suspension for fluorescent magnetic particle testing
- Oil based
- well suited for fine defects, high sensitivity
- Settling volume (1h) 0.30 - 0.40 ml/ 100ml
- Average grain size da 5 µm
- Yellow - green crack indication

Minimum shelf life / temperatures

Aerosole / Bulk:
3 years at storage temperature
Storage: + 5 °C - + 45 °C
Application: - 10 °C - + 50 °C



Approvals / Specification



- EN ISO 9934-2
- AMS 3044
- AMS 3045
- AMS 3046 (nur Aerosol)
- AMS 2641 - Type 2
- ASTM E709
- ASTM E1444/1444M
- ASME Code V, Art. 7
- ASME B & PV Code, Sec V
- RCC-M

Further information

Process description according to EN ISO 9934-1 available on request or at www.mr-chemie.de. For further information, please refer to our Safety Data Sheet and 3.1 Certificate. For necessary and supplementary test accessories, visit our website or contact our staff.

Suggested products

Pre-cleaner: MR[®] 71, MR[®] 79, MR[®] 85, MR[®] 88, MR[®] 3001, MR[®] 3002
Test body: Reference block 1 and 2, test block
Devices: All MR[®] units for magnetic particle testing
Cleaner: MR[®] 71

Delivery form



****Technische Änderungen vorbehalten!****